

Ultem* Resin STM1500

Americas: COMMERCIAL

Siloxane polyetherimide block copolymer. Wire and cable use. Strength and flexibility.

Property

TYPICAL PROPERTIES ⁽¹⁾			
	Value	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	28	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Flexural Modulus, 2.6 mm/min, 100 mm span	380	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	26	mg/1000cy	ASTM D 1044
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Moisture Absorption (est)	<0	%	ASTM D 570
Melt Flow Rate, 295°C/6.6 kgf	12	g/10 min	ASTM D 1238
Matrix Tg	168	°C	DMA
Halogen Content	0	%	SABIC Method
ELECTRICAL			
Volume Resistivity	4.1E+16	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+15	Ohm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	16.1	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	16.3	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.01	-	ASTM D 150
Relative Permittivity, 100 kHz	2.7	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.01	-	ASTM D 150
Dissipation Factor, 100 kHz	0.0056	-	ASTM D 150
FLAME CHARACTERISTICS			
OSU peak heat release rate (5 minute test)	140	kW/m ²	FAR 25.853
Oxygen Index (LOI)	46	%	ASTM D 2863
WIRE AND CABLE - UL 1581 tested on 2.0mm wire with 0.12mmx20 stranded copper			
Cable Wall Thickness	10	mil	-
Tensile Strength (Wire/Cable), break	-	-	SABIC (UL1561)
Initial	37	MPa	-
Aged 1 week at 135°C	38	MPa	-
Tensile Strength Retention	102	%	-
Tensile Elongation (Wire/Cable), break	-	-	SABIC (UL1561)
Initial	400	%	-
Aged 1 week at 135°C	370	%	-
Tensile Elongation Retention	94	%	-
COMBUSTION CORROSIVITY			
Corrosion, 1 hr (2500 angstroms max)	40	angstrom	ASTM E5.2170
Corrosion, 24 hrs	122	angstrom	ASTM E5.2170
Corrosion, 6 days	183	angstrom	ASTM E5.2170

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	105	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	300 - 320	°C
Nozzle Temperature	300 - 320	°C
Front - Zone 3 Temperature	295 - 315	°C
Middle - Zone 2 Temperature	295 - 315	°C
Rear - Zone 1 Temperature	295 - 315	°C
Mold Temperature	65 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 100	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm

Source GMD, last updated:01/05/2000

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Ultem is a trademark of the SABIC Innovative Plastics Company